

PRODUCT NAME

Fence and Shed Paint

ORIGINALLY ISSUED

04/12/2017

VERSION

1.0

PRODUCT CODE

DEC903

VERSION DATE

04/12/2017



PRODUCT DESCRIPTION

A Water Based long lasting coating for use over fencing and other rough sawn garden timber to colour and protect.

Low Odour.

Safe to use around plants and pets.

Non-drip formulation.

Suitable for exterior wood.

Low sheen dependant on substrate.

This paint can't be applied in the rain. It needs to be a warm, dry day with temperatures above 10°C. Cold weather will stop it from properly drying and impact adhesion.

This paint isn't suitable for decking.



IMPORTANT INSTRUCTIONS BEFORE USE

- Read and follow SDS, TDS and label instructions
- Stir all paints thoroughly before use
- Always use the same batch number on the same job
- Check colour & sheen. HMG will not accept any discrepancies arising after use
- Filter the product immediately before use
- Reduce emissions and maintain quality by replacing tin lid after use
- If in any doubt speak HMG Technical Service Department on (0161) 205 7631



MAXIMUM VOC CONTENT (RFU)

0.060Kg/L



COLOUR RANGE

- HMG Essentials and RAL as standard. Special Colours and Colour Matching on Request



PACKAGING

5ltr and 10 ltr packs.



GENERAL INFORMATION

Coverage 15-20 square metres per litre dependant on substrate.
Flashpoint X°C
Storage Store between 5°C - 38°C. When not in use, cans must be kept sealed
Shelf Life 12 months from delivery date in original sealed containers



ADDITIONAL TECHNICAL INFORMATION

Application temperature 10-32°C

Do not freeze.



CLEANING

Ensure substrate is clean and dry.

Please refer to our website for Knowledge Base article Prep-Cleaning Techniques (KNB0009) and Preparatory Cleaners from the Product Guide.



SURFACE PREPARATION

Please refer to Knowledge Base on our website for details on Surface Preparation.



HEALTH AND SAFETY

- Refer to Health & Safety Data Sheet prior to use.

APPLICATION METHODS






MIXING RATIO

BRUSH		ROLLER					
Base	rfu	Base	rfu				



VISCOSITY

3000-4000 cps	Brookfield Viscometer	3000-4000cps	Brookfield Viscometer				
---------------	-----------------------	--------------	-----------------------	--	--	--	--

	DRYING TIME							
	Touch dry Hard dry	30-40mins@20°C 2-4hrs@20°C	Touch dry Hard dry	30-40mins@20°C 2-4hrs@20°C				
	WET FILM THICKNESS*							
	100microns		100microns					
	DRY FILM THICKNESS*							
	20-25microns per coat		20-25microns per coat					
<p><small>* - HMG Technical Data Sheets indicate a Dry Film Thickness that will be achieved when applying a particular Wet Film Thickness. These values are a guide only and are not to be used as specifications. Film thickness will vary depending on actual use and specification. Great care should be taken to achieve the dft stated in the agreed specification and to avoid areas of excessively low or high thickness.</small></p>								

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.