

# BDX Synthetic Primer

## Description

BDX Synthetic Primer is a high build anti corrosive, single pack alkyd primer for use under all HMG Synthetic topcoats.

## Features

BDX Synthetic Primer is high build and excellent sand ability after short drying period with outstanding application and scratch filling properties.

Suitable for use to suitably prepared structural steel, chassis, steel fabrication by brush or compliant spray.

- Allow hard dry prior to sanding.
- Suitable for use under HMG C71 Speedline
- Available in White, Lt Grey, Dk Grey and Red Oxide.
- Coverage: 16.6m<sup>2</sup> per litre at 55 microns DFT
- Touch dry: 4 hours mins at 20°C
- Thinner: HMG 2611, 2612

All HMG Paints products are manufactured in Manchester, UK under the auspices of an ISO 9001 management system and are Made in Britain accredited.



## Substrates

Suitably prepared Steel, Aluminium and some Plastics, dry, clean & free of grease oils and dust.

Not suitable for coating over bitumen or chlorinated rubber coatings. Suitability with existing coatings to be checked with test application prior to use.

## Important Information Before Use

Read and follow SDS, TDS, and label instructions. Stir paint thoroughly before use. Always use the same batch number on the same job. Check colour and sheen, HMG will not accept any discrepancies arising after use.

Filter the product immediately before use. If in doubt, contact HMG Technical Service Department on 0161 205 7631.

## Application

### Method

Brush or Compliant Spray Gun

### Surface Preparation

Please refer to our web site for:

Knowledge Base article Prep Cleaning Techniques (KNB0009).

Knowledge Base article Surface Preparation & Product Application (KNB0029).

Knowledge Base article Pictorial Surface Preparation Standards for Painting Steel Surfaces (KNB0026).

### Application Climate

Substrate temperature should be 5°C or above for application and during cure, and a minimum of 3°C above the dew point. Adequate dry air ventilation should be supplied during drying.

# BDX Synthetic Primer

## Application Information

Substrate temperature should be 5°C or above for application and during cure, and a minimum of 3° above the dew point. Adequate dry air ventilation should be supplied during drying.

## Technical Information

Theoretical Coverage (approx) at 20 microns DFT	16.6m <sup>2</sup> per litre	Number of Coats (Guide Only)	Brush - 1 Coat Spray - 1 Light + 1 Full
Drying time at 20°C (May vary with film build and temperature)	Touch Dry - 4 Hours Hard Dry - 24 Hours	Application	Brush or Compliant
Suggested Primer	ST3000 2K Etch Primer	Spray Gun Setup	Compliant 1.6 - 1.8
Thinner	2611 or 2612	Wet Film (WFT)	100 microns
Thinning	Brush up to 5% 2612 Compliant Spray up to 10% 2611/2612	Dry Film (DFT)	55 microns
Flash Point	38°C	Pot Life	N/A
Volume Solids	55%	Recoat / Overcoat	After 16 - 48 hrs depending on film build and drying conditions
Maximum VOC (RFU)	480g/l	Finish	N/A
Regulation / Compliance	2004/42 IIB (C) 540	Available Pack Sizes	1 Litre & 5 Litre

## Colour Range

Dark Grey, Light Grey, Red Oxide and Off White.

## General Specification

### Bare substrates

**Mild steel** – Remove millscale and thoroughly degrease using suitable HMG Prep Clean. Abrade with P80 – P180 if necessary, prior to application of primer.

**Shot Blasted Steel** – Remove all traces of blast grit/sand prior to application of primer.

**Aluminium** – Abrade with P180 – P320, degrease with suitable HMG Prep Clean prior to application of primer.

**Galvanised Steel** – Degrease with suitable HMG Prep Clean, apply HMG Mordant Wash, apply HMG Etch Primer and if required HMG Primer.

### Previously Painted

High pressure wash to remove all loose debris and poorly adhered previous coatings to remove all salts and other contaminants.

Degrease using suitable HMG Degreaser 2800 to remove grease and oils not removed with pressure washing alone. Existing coatings to be well adhered with all edges tight and well feathered. Rust/corrosion to be removed back to

# BDX Synthetic Primer

clean metallic appearance.

Abrade to provide good adhesion.

Wipe over with degreaser to remove loose debris from abrasion.

Substrate to be clean, free of grease, oils, dust and completely dry prior to application.

For full surface preparation please refer to our web site for Knowledge Base article Prep Cleaning Techniques (KNB0009) and Preparatory Cleaners from the Product Guide. If in doubt speak to HMG Technical Department on 0161 205 7631.

## Health, Safety & Environmental

Refer to SDS and tin label prior to use. Suitable respiratory equipment should be worn when spraying. Contaminated rags, spray booth filters or other substrates should be segregated from other chemical waste, soaked with water or disposed of in a non-combustible container with tight fitting lid. Reduce emissions and maintain quality by replacing tin lid after use. Store between 5°C & 25°C. When not in use, cans must be kept sealed. Shelf Life for this product is 12 months from delivery date in original sealed containers.

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. However, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability and completeness of such information for their own particular use. For professional use only.